



OPC CLINKER SPECIFICATION

OPC CLINKER

Product Details

Product :

OPC CLINKER

Usage

Cement Companies

Packing

Bulk

Bulk in jumbo bags(1,1.5,2 tons)



Components	Typical Result	Standard Deviation
SiO ₂ (%)	21.70	0.30
Al ₂ O ₃ (%)	4.80	0.30
Fe ₂ O ₃ (%)	4.30	0.20
CaO (%)	65.20	0.50
MgO (%)	2.30	0.10
K ₂ O	0.65	0.10
Na ₂ O	0.20	0.10
SO ₃ (%)	0.10-1.00	-
L.O.I	0.20-0.80	-
I.R	0.30	0.10
L.S.F	94.00	1.20
F.CaO	1.30	0.35
C ₃ S	61.00	1.50
C ₂ S	16.00	1.00
C ₃ A	5.50	-
C ₄ AF	13.10	1.00
Litre Weight	1320	100
SM	2.35	0.10
AM	1.15	0.10